

## GREENBAG

PROPERTIES	VALUE	UNIT	NORM
Thickness	200	microns	ISO 4591
Aspect	Normal		EN 13207

### Mechanical Properties

#### Tensile Strength at Break

MD	24	MPa	EN ISO 527-3
TD	23	MPa	EN ISO 527-3

#### Elongation at Break

MD	900	%	EN ISO 527-3
TD	900	%	EN ISO 527-3

#### Tensile Strength at Yield

MD	12	MPa	EN ISO 527-3
TD	11	MPa	EN ISO 527-3

#### Dart Test F 50

Side	> 900	cN	ISO 7765-1
Fold	770	cN	ISO 7765-1

### Optical Properties

Relative Transmission of Light	≤ 1 E-2	EN 13655
--------------------------------	---------	----------

### Other Properties

#### Additional Properties